

Air leak pressure test

Material	Gloves Thickness					
	15 MIL		25 MIL		30 MIL	
	P MAX	P MIN	P MAX	P MIN	P MAX	P MIN
Hypalon	20	10	20	10	20	10
Butyl	15	7.5	15	7.5	15	7.5

Pressures are in millibars
 Pressure minimum is after 1-hour leak test